


Voltera Spot Blender VA152 help to melt in clear coat blends, dry overspray from solvent basecoat. Using light coats of VA152, it dissolves rough overspray edges, new & existing finishes.



COMPONENTS

VA152 Spot Blender

SURFACE PREPARATION




Use degreaser to remove contaminations such as silicone and wax.

APPLICATION



RP: 1.2-1.4mm 24-28psi
HVLP: 1.2-1.4mm 26-29psi
Please refer to gun manufacturer for proper spray pressure recommendations.



Spray slightly one coat over the overspray area with Thinner SRA right after the finish. Second coat in 20 seconds.

NOTES

- 2 year shelf life

FOR PROFESSIONAL USE ONLY

The information presented on this Technical Data Sheet is determined by industry knowledge and current regulations. It is the responsibility of the applicator and purchaser to understand and abide by the requirements of any and all local regulations. Voltera Coatings is not to be held responsible, nor holds any liability for product failure, rework, damage or performance issues based on improper application of the product. Always reference the most up-to-date version of the Material Data Sheet and the Technical Data Sheet before applying the product.